





SCI Engineered Materials



Common Uses
Pigment (White)
UV Blocking Pigments (Sunscreen)
Dielectric Mirrors
Photocatalyst

Melting Point	1,843 °C (3,349 °F; 2,116 K)
Boiling Point	2,972 °C (5,382 °F; 3,245 K)
Crystal Forms	Tetragonal, Orthorhombic, Monoclinic, Cubic
Molar Mass	79.866 g/mol
Common Mineral Names	Rutile, Anatase, Brookite
Refractive Index	2.488 (anatase) 2.583 (brookite) 2.609 (rutile)



By Geek3 - Own work, CC BY-SA 4.0,
<https://commons.wikimedia.org/w/index.php?curid=54912389>